

APPLICATION
FOR
UNITED STATES LETTERS PATENT

TITLE: CELLULOSIC AND LIGNOCELLULOSIC MATERIALS
AND COMPOSITIONS AND COMPOSITES MADE
THEREFROM

APPLICANT: DR. MARSHALL MEDOFF AND ARTHUR P. LAGACE

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No. EE647282521US

I hereby certify under 37 CFR §1.10 that this correspondence is being deposited with the United States Postal Service as Express Mail Post Office to Addressee with sufficient postage on the date indicated below and is addressed to the Commissioner for Patents, Washington, D.C. 20231.

January 30, 2001

Date of Deposit

Peter Consoli

Signature

PETER CONSOLI

Typed or Printed Name of Person Signing Certificate

CELLULOSIC AND LIGNOCELLULOSIC MATERIALS
AND COMPOSITIONS AND COMPOSITES MADE THEREFROM

5 Cross Reference to Related Applications

2-02
mm

This application is a continuation-in-part of U.S. Patent Application Serial No. 09/337,580, filed June 22, 1999, ^{and now U.S. Patent No. 6,207,729} which is a continuation in part of U.S. Patent Application No. 08/961,863, filed October 31, 1997, now
10 issued as U.S. Patent No. 5,973,035; is a continuation-in-part of U.S. Patent Application Serial No. 09/338,209, filed June 22, 1999, which is a continuation-in-part of U.S. Patent Application No. 08/921,807, filed September 2, 1997, now issued as U.S. Patent No. 5,952,105; and is a
15 continuation in part of U.S. Patent Application Serial No. 09/290,031, filed April 9, 1999, ^{now U.S. Pat. No. 6,258,876} which is a division of U.S. Patent Application No. 08/961,863, filed October 31, 1997, now issued as U.S. Patent No. 5,973,035.

20 Background of the Invention

The invention relates to texturized cellulosic or lignocellulosic materials and compositions and composites made from such texturized materials.

Cellulosic and lignocellulosic materials are
25 produced, processed, and used in large quantities in a number of applications. Once used, these materials are usually discarded. As a result, there is an ever-increasing amount of waste cellulosic and lignocellulosic material.

30 Summary of the Invention

In general, the invention features texturized cellulosic or lignocellulosic materials and compositions and composites made therefrom.

The texturized fibrous material can have a bulk density less than about 0.5 grams per cubic centimeter, or even less than about 0.2 g/cm³.

Compositions that include the texturized fibrous materials described above, together with a chemical or chemical formulation (e.g., a pharmaceutical such as an antibiotic or contraceptive, optionally with an excipient; an agricultural compound such as a fertilizer, herbicide, or pesticide; or a formulation that includes enzymes) are also within the scope of the invention, as are compositions that include the texturized fibrous materials and other liquid or solid ingredients (e.g., particulate, powdered, or granulated solids such as plant seed, foodstuffs, or bacteria).

Composites that include thermoplastic resin and the texturized fibrous materials are also contemplated. The resin can be, for example, polyethylene, polypropylene, polystyrene, polycarbonate, polybutylene, a thermoplastic polyester, a polyether, a thermoplastic polyurethane, polyvinylchloride, or a polyamide, or a combination of two or more resins.

In some cases, at least about 5% by weight (e.g., 5%, 10%, 25%, 50%, 75%, 90%, 95%, 99%, or about 100%) of the fibrous material included in the composites is texturized.

The composite may include, for example, about 30% to about 70% by weight resin and about 30% to about 70% by weight texturized fibrous material, although proportions outside of these ranges may also be used. The composites can be quite strong, in some cases having a flexural strength of at least about 6,000 to 10,000 psi.

In another embodiment, the invention features a composite including a resin, such as a thermoplastic resin, and at least about 2% by weight, more preferably at least about 5% by weight, texturized cellulosic or lignocellulosic fiber. The invention also features a composite that includes polyethylene and at least about 50% by weight texturized cellulosic or lignocellulosic fiber.

The invention further features composites, including a resin and cellulosic or lignocellulosic fiber, that have flexural strengths of at least about 3,000 psi, or tensile strengths of at least about 3,000 psi.

In addition, the invention features a process for manufacturing a composite; the process includes shearing cellulosic or lignocellulosic fiber to form texturized cellulosic or lignocellulosic fiber, then combining the texturized fiber with a resin. A preferred method includes shearing the fiber with a rotary knife cutter. The invention also features a process for manufacturing a composite that includes shearing cellulosic or lignocellulosic fiber and combining the fiber with a resin.

The composites can also include inorganic additives such as calcium carbonate, graphite, asbestos, wollastonite, mica, glass, fiber glass, chalk, talc, silica, ceramic, ground construction waste, tire rubber powder, carbon fibers, or metal fibers (e.g., stainless steel or aluminum). The inorganic additives can represent about 0.5% to about 20% of the total weight of the composite.

The composite can be in the form of, for example, a pallet (e.g., an injection molded pallet), pipes, panels, decking materials, boards, housings, sheets, poles, straps, fencing, members, doors, shutters, awnings, shades, signs,

frames, window casings, backboards, wallboards, flooring,
 tiles, railroad ties, forms, trays, tool handles, stalls,
 bedding, dispensers, staves, films, wraps, totes, barrels,
 boxes, packing materials, baskets, straps, slips, racks,
 5 casings, binders, dividers, walls, indoor and outdoor
 carpets, rugs, wovens, and mats, frames, bookcases,
 sculptures, chairs, tables, desks, art, toys, games,
 wharves, piers, boats, masts, pollution control products,
 septic tanks, automotive panels, substrates, computer
 10 housings, above- and below-ground electrical casings,
 furniture, picnic tables, tents, playgrounds, benches,
 shelters, sporting goods, beds, bedpans, thread, filament,
 cloth, plaques, trays, hangers, servers, pools, insulation,
 caskets, bookcovers, clothes, canes, crutches, and other
 15 construction, agricultural, material handling,
 transportation, automotive, industrial, environmental,
 naval, electrical, electronic, recreational, medical,
 textile, and consumer products. The composites can also be
 in the form of a fiber, filament, or film.

20 The terms "texturized cellulosic or lignocellulosic
 material" and "texturized fibrous material" as used herein,
 mean that the cellulosic or lignocellulosic material has
 been sheared to the extent that its internal fibers are
 substantially exposed. At least about 50%, more preferably
 25 at least about 70%, of these fibers have a length/diameter
 (L/D) ratio of at least 5, more preferably at least 25, or
 at least 50. An example of texturized cellulosic material
 is shown in Fig. 1.

The texturized fibrous materials of the invention
 30 have properties that render them useful for various
 applications. For example, the texturized fibrous materials

have absorbent properties, which can be exploited, for example, for pollution control. The fibers are generally biodegradable, making them suitable, for example, for drug or chemical delivery (e.g., in the treatment of humans, 5 animals, or in agricultural applications). The texturized fibrous materials can also be used to reinforce polymeric resins.

Those composites that include texturized fibrous material and resin are strong, lightweight, and inexpensive. 10 The raw materials used to make the composites are available as virgin or recycled materials; for example, they may include discarded containers composed of resins, and waste cellulosic or lignocellulosic fiber.

Other features and advantages of the invention will 15 be apparent from the following detailed description, and from the claims.

Brief Description of the Drawing

Fig. 1 is a photograph of a texturized newspaper, 20 magnified fifty times.

Detailed Description of the Invention

Examples of cellulosic raw materials include paper and paper products such as newsprint, poly-coated paper, and 25 effluent from paper manufacture; examples of lignocellulosic raw materials include wood, wood fibers, and wood-related materials, as well as materials derived from kenaf, grasses, rice hulls, bagasse, cotton, jute, other stem plants (e.g., hemp, flax, bamboo; both bast and core fibers), leaf plants 30 (e.g., sisal, abaca), and agricultural fibers (e.g., cereal straw, corn cobs, rice hulls, and coconut hair). Aside from

virgin raw materials, post-consumer, industrial (e.g., offal), and processing waste (e.g., effluent) can also be used as fiber sources.

5 Preparation of Texturized Fibrous Material

If scrap cellulosic or lignocellulosic materials are used, they should be clean and dry. The raw material can be texturized using any one of a number of mechanical means, or combinations thereof. One method of texturizing includes
10 first cutting the cellulosic or lignocellulosic material into 1/4- to 1/2-inch pieces, if necessary, using a standard cutting apparatus. Counter-rotating screw shredders and segmented rotating screw shredders such as those manufactured by Munson (Utica, NY) can also be used, as can
15 a standard document shredder as found in many offices.

The cellulosic or lignocellulosic material is then sheared with a rotary cutter, such as the one manufactured by Sprout, Waldron Companies, as described in Perry's Chem. Eng. Handbook, 6th Ed., at 8-29 (1984). Although other
20 settings can be used, the spacing between the rotating knives and bed knives of the rotary cutter is typically set to 0.020" or less, and blade rotation is set to 750 rpm or more. The rotary cutter can be cooled to 100°C or lower during the process, for example, using a water jacket.

The texturized material is passed through a
25 discharge screen. Larger screens (e.g., up to 6 mm) can be used in large-scale production. The cellulosic or lignocellulosic feedstock is generally kept in contact with the blades of the rotary cutter until the fibers are pulled
30 apart; smaller screens (e.g., 2 mm mesh) provide longer residence times and more complete texturization, but can

result in lower length/diameter (L/D) aspect ratios. A vacuum drawer can be attached to the screen to maximize and maintain fiber length/diameter aspect ratio.

The texturized fibrous materials can be directly
5 stored in sealed bags or may be dried at approximately 105°C for 4-18 hours (e.g., until the moisture content is less than about 0.5%) immediately before use. Fig. 1 is an SEM photograph of texturized newspaper.

Alternative texturizing methods include stone
10 grinding, mechanical ripping or tearing, and other methods whereby the material's internal fibers can be exposed (e.g., pin grinding, air attrition milling).

Uses of Texturized Fibrous Material

15 Texturized fibrous materials and compositions and composites of such fibers with other chemicals and chemical formulations can be prepared to take advantage of the material's properties. The materials can be used to absorb chemicals, for example, potentially absorbing many times
20 their own weight. Thus, the materials could, for instance, be used to absorb spilled oil, or for clean-up of environmental pollution, for example, in water, in the air, or on land. Similarly, the material's absorbent properties, together with its biodegradability, also make them useful
25 for delivery of chemicals or chemical formulations. For example, the materials can be treated with solutions of enzymes or pharmaceuticals such as antibiotics, nutrients, or contraceptives, and any necessary excipients, for drug delivery (e.g., for treatment of humans or animals, or for
30 use as or in animal feed and/or bedding), as well as with solutions of fertilizers, herbicides, or pesticides. The

materials can optionally be chemically treated to enhance a specific absorption property. For example, the materials can be treated with silanes to render them lipophilic.

Compositions including texturized materials combined with liquids or particulate, powdered, or granulated solids can also be prepared. For example, texturized materials can be blended with seeds (i.e., with or without treatment with a solution of fertilizer, pesticides, etc.), foodstuffs, or bacteria (e.g., bacteria that digest toxins). The ratio of fibrous materials to the other components of the compositions will depend on the nature of the components and readily be adjusted for a specific product application.

In some cases, it may be advantageous to associate the texturized fibrous materials, or compositions or composites of such materials, with a structure or carrier such as a netting, a membrane, a flotation device, a bag, a shell, or a biodegradable substance. Optionally, the structure of carrier may itself be made of a texturized fibrous material (e.g., a material of the invention), or a composition or composite thereof.

Composites of Texturized Fibrous Material and Resin

Texturized fibrous materials can also be combined with resins to form strong, lightweight composites. Materials that have been treated with chemicals or chemical formulations, as described above, can similarly be combined with biodegradable or non-biodegradable resins to form composites, allowing the introduction of, for example, hydrophilic substances into otherwise hydrophobic polymer matrices. Alternatively, the composites including

texturized fibrous materials and resin can be treated with chemicals or chemical formulations.

The texturized cellulosic or lignocellulosic material provides the composite with strength. The
5 composite may include from about 10% to about 90%, for example from about 30% to about 70%, of the texturized cellulosic or lignocellulosic material by weight.

The resin encapsulates the texturized cellulosic or lignocellulosic material in the composites, and helps
10 control the shape of the composites. The resin also transfers external loads to the fibrous materials and protects the fiber from environmental and structural damage.

Composites can include, for example, about 10% to about 90%, more preferably about 30% to about 70%, by weight, of
15 the resin.

Resins are used in a variety of applications, for example, in food packaging. Food containers made of resins are typically used once, then discarded. Examples of resins that are suitably combined with texturized fibers include
20 polyethylene (including, e.g., low density polyethylene and high density polyethylene), polypropylene, polystyrene, polycarbonate, polybutylene, thermoplastic polyesters (e.g., PET), polyethers, thermoplastic polyurethane, PVC, polyamides (e.g., nylon) and other resins. It is preferred
25 that the resins have a low melt flow index. Preferred resins include polyethylene and polypropylene with melt flow indices of less than 3 g/10 min, and more preferably less than 1 g/10 min.

The resins can be purchased as virgin material, or
30 obtained as waste materials, and can be purchased in pelletized or granulated form. One source of waste resin is

used polyethylene milk bottles. If surface moisture is present on the pelletized or granulated resin, however, it should be dried before use.

The composites can also include coupling agents.

- 5 The coupling agents help to bond the hydrophilic fibers to the hydrophobic resins. Examples of coupling agents include maleic anhydride modified polyethylenes, such those in the FUSABOND® (available from DuPont, Delaware) and POLYBOND® (available from Uniroyal Chemical, Connecticut) series. One
10 suitable coupling agent is a maleic anhydride modified high density polyethylene such as FUSABOND® MB 100D.

- The composites can also contain additives known to those in the art of compounding, such as plasticizers, lubricants, antioxidants, opacifiers, heat stabilizers,
15 colorants, flame retardants, biocides, impact modifiers, photostabilizers, and antistatic agents.

- The composites can also include inorganic additives such as calcium carbonate, graphite, asbestos, wollastonite, mica, glass, fiber glass, chalk, silica, talc, ceramic,
20 ground construction waste, tire rubber powder, carbon fibers, or metal fibers (e.g., aluminum, stainless steel). When such additives are included, they are typically present in quantities of from about 0.5% up to about 20-30% by weight. For example, submicron calcium carbonate can be
25 added to the composites of fiber and resin to improve impact modification characteristics or to enhance composite strength.

Preparation of Compositions

- 30 Compositions containing the texturized cellulosic or lignocellulosic materials and chemicals, chemical

formulations, or other solids can be prepared, for example, in various immersion, spraying, or blending apparatuses, including, but not limited to, ribbon blenders, cone blenders, double cone blenders, and Patterson-Kelly "V" blenders.

For example, a composition containing 90% by weight texturized cellulosic or lignocellulosic material and 10% by weight ammonium phosphate or sodium bicarbonate can be prepared in a cone blender to create a fire-retardant material for absorbing oil.

Preparation of Composites of Texturized Fiber and Resin

Composites of texturized fibrous material and resin can be prepared as follows. A standard rubber/plastic compounding 2-roll mill is heated to 325-400°F. The resin (usually in the form of pellets or granules) is added to the heated roll mill. After about 5 to 10 minutes, the coupling agent is added to the roll mill. After another five minutes, the texturized cellulosic or lignocellulosic material is added to the molten resin/coupling agent mixture. The texturized material is added over a period of about 10 minutes.

The composite is removed from the roll mill, cut into sheets and allowed to cool to room temperature. It is then compression molded into plaques using standard compression molding techniques.

Alternatively, a mixer, such as a Banbury internal mixer, is charged with the ingredients. The ingredients are mixed, while the temperature is maintained at less than about 190°C. The mixture can then be compression molded.

In another embodiment, the ingredients can be mixed in an extruder mixer, such as a twin-screw extruder equipped with co-rotating screws. The resin and the coupling agent are introduced at the extruder feed throat; the texturized
5 cellulosic or lignocellulosic material is introduced about 1/3 of the way down the length of the extruder into the molten resin. The internal temperature of the extruder is maintained at less than about 190°C. At the output, the composite can be, for example, pelletized by cold strand
10 cutting.

Alternatively, the mixture can first be prepared in a mixer, then transferred to an extruder.

In another embodiment, the composite can be formed into fibers, using fiber-forming techniques known to those
15 in the art, or into filaments for knitting, warping, weaving, braiding, or making non-wovens. In a further embodiment, the composite can be made into a film.

Properties of the Composites of Texturized Fibrous Material 20 and Resin

The resulting composites include a network of fibers, encapsulated within a resin matrix. The fibers form a lattice network, which provides the composite with strength. Since the cellulosic or lignocellulosic material
25 is texturized, the amount of surface area available to bond to the resin is increased, in comparison to composites prepared with un-texturized cellulosic or lignocellulosic material. The resin binds to the surfaces of the exposed fibers, creating an intimate blend of the fiber network and
30 the resin matrix. The intimate blending of the fibers and the resin matrix further strengthens the composites.

Uses of the Composites of Texturized Fibrous Material and Resin

The resin/fibrous material composites can be used in
5 a number of applications. The composites are strong and
light weight; they can be used, for example, as wood
substitutes. The resin coating renders the composites
water-resistant, so they may be used in outdoor
applications. For example, the composites may be used to
10 make pallets, which are often stored outdoors for extended
periods of time, wine staves, rowboats, furniture, skis, and
oars. Many other uses are contemplated, including panels,
pipes, decking materials, boards, housings, sheets, poles,
straps, fencing, members, doors, shutters, awnings, shades,
15 signs, frames, window casings, backboards, wallboards,
flooring, tiles, railroad ties, forms, trays, tool handles,
stalls, bedding, dispensers, staves, films, wraps, totes,
barrels, boxes, packing materials, baskets, straps, slips,
racks, casings, binders, dividers, walls, indoor and outdoor
20 carpets, rugs, wovens, and mats, frames, bookcases,
sculptures, chairs, tables, desks, art, toys, games,
wharves, piers, boats, masts, pollution control products,
septic tanks, automotive panels, substrates, computer
housings, above- and below-ground electrical casings,
25 furniture, picnic tables, tents, playgrounds, benches,
shelters, sporting goods, beds, bedpans, thread, filament,
cloth, plaques, trays, hangers, servers, pools, insulation,
caskets, bookcovers, clothes, canes, crutches, and other
construction, agricultural, material handling,
30 transportation, automotive, industrial, environmental,
naval, electrical, electronic, recreational, medical,

textile, and consumer products. Numerous other applications are also envisioned. The composites may also be used, for example, as the base or carcass for a veneer product. Moreover, the composites can be, for example, surface
5 treated, grooved, milled, shaped, imprinted, textured, compressed, punched, or colored. The surface of the composites can be smooth or rough.

The following examples illustrate certain embodiments and aspects of the present invention and not to
10 be construed as limiting the scope thereof.

Examples

Example 1

A 1500 pound skid of virgin, half-gallon juice
15 cartons made of polycoated white kraft board was obtained from International Paper. Each carton was folded flat.

The cartons were fed into a 3 hp Flinch Baugh shredder at a rate of approximately 15 to 20 pounds per hour. The shredder was equipped with two rotary blades,
20 each 12" in length, two fixed blades, and a 0.3" discharge screen. The gap between the rotary and fixed blades was 0.10".

The output from the shredder, consisting primarily of confetti-like pieces, about 0.1" to 0.5" in width and
25 about 0.25" to 1" in length, was then fed into a Thomas Wiley Mill Model 2D5 rotary cutter. The rotary cutter had four rotary blades, four fixed blades, and a 2 mm discharge screen. Each blade was approximately 2" long. The blade gap was set at 0.020".

30 The rotary cutter sheared the confetti-like pieces across the knife edges, tearing the pieces apart and

releasing a finely texturized fiber at a rate of about one pound per hour. The fiber had an average minimum L/D ratio of between five and 100 or more. The bulk density of the texturized fiber was on the order of 0.1 g/cc.

5

Example 2

Composites of texturized fiber and resin were prepared as follows. A standard rubber/plastic compounding 2-roll mill was heated to 325-400°F. The resin (usually in the form of pellets or granules) was added to the heated roll mill. After about 5 to 10 minutes, the resin banded on the rolls (i.e., it melted and fused on the rolls). The coupling agent was then added to the roll mill. After another five minutes, the texturized cellulosic or lignocellulosic material was added to the molten resin/coupling agent mixture. The cellulosic or lignocellulosic fiber was added over a period of about 10 minutes.

The composite was then removed from the roll mill, cut into sheets, and allowed to cool to room temperature. Batches of about 80 g each were compression molded into 6" x 6" x 1/8" plaques using standard compression molding techniques.

One composition contained the following ingredients:

25

Composition No. 1

<u>Ingredient</u>	<u>Amount (g)</u>
High density polyethylene ¹	160
Old newspaper ²	240
Coupling agent ³	8
¹ Marlex 16007	
² Texturized using rotary cutter with 2 mm mesh	

30

³ FUSABOND® 100D

The plaques were machined into appropriate test specimens and tested according to the procedures outlined in the method specified. Three different specimens were tested 5 for each property, and the mean value for each test was calculated. The properties of Composition No. 1 are as follows:

Flexural strength (10^3 psi)	9.81 (ASTM D790)
Flexural modulus (10^5 psi)	6.27 (ASTM D790)

A second composition contains the following ingredients:

Composition No. 2

	<u>Ingredient</u>	<u>Amount (g)</u>
15	High density polyethylene ¹	160
	Old magazines ²	240
	Coupling agent ³	8

The properties of Composition No. 2 are as follows:

	Flexural strength (10^3 psi)	9.06 (ASTM D790)
20	Flexural modulus (10^5 psi)	6.78 (ASTM D790)

A third composition contains the following ingredients:

Composition No. 3

	<u>Ingredient</u>	<u>Amount (g)</u>
25	HDPE ¹	160
	Fiber paper ²	216
	3.1 mm texturized kenaf	24
	Coupling agent ³	8

The properties of Composition No. 3 are as follows:

Flexural strength (10^3 psi)	11.4 (ASTM D790)
Flexural modulus (10^5 psi)	6.41 (ASTM D790)

5 A fourth composition contains the following ingredients:

Composition No. 4

	<u>Ingredient</u>	<u>Amount (g)</u>
	SUPERFLEX™ CaCO_3	33
10	Fiber ^{2,4}	67
	HDPE (w/3% compatibilizer) ^{1,3}	100

⁴ Virgin polycoated milk cartons

15 The properties of Composition No. 4 are as follows:

	Flexural strength (10^5 psi)	8.29 (ASTM D790)
20	Ultimate elongation (%)	<5 (ASTM D638)
	Flexural modulus (10^5 psi)	10.1 (ASTM D790)
	Notch Izod (ft-lb/in)	1.39 (ASTM D256-97)

25 A fifth composition contains the following ingredients:

Composition No. 5

	<u>Ingredient</u>	<u>Amount (parts)</u>
30	SUPERFLEX™ CaCO_3	22
	Fiber ^{2,4}	67
	HDPE (w/3% compatibilizer) ^{1,3}	100

35 The properties of Composition No. 5 are as follows:

Flexural strength (10^5 psi)	8.38 (ASTM D790)
---------------------------------	------------------

Ultimate elongation (%)	<5 (ASTM D638)
Flexural modulus (10 ⁵ psi)	9.86 (ASTM D790)
Notch Izod (ft-lb/in)	1.37 (ASTM D256-97)

A sixth composition contains the following ingredients:

10 Composition No. 6

<u>Ingredient</u>	<u>Amount (parts)</u>
ULTRAFLEX TM CaCO ₃	33
Fiber ^{2,4}	67
HDPE/compatibilizer ^{1,3}	100

15 The properties of Composition No. 6 are as follows:

Flexural strength (10 ⁵ psi)	7.43 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural modulus (10 ⁵ psi)	11.6 (ASTM D790)
Notch Izod (ft-lb/in)	1.27 (astm D256-97)

25 A seventh composition contains the following ingredients:

Composition No. 7

<u>Ingredient</u>	<u>Amount (pbw)</u>
HDPE (w/3% compatibilizer) ^{3,5}	60
Kraftboard ²	40

30 ⁵ HDPE with melt-flow index <1

The properties of Composition No. 7 are as follows:

Flexural Strength (10 ⁵ psi)	7.79 (ASTM D790)
Ultimate elongation (%)	<5 (ASTM D638)
Flexural Modulus (10 ⁵ psi)	7.19 (ASTM D790)

35 other embodiments are within the claims.